



Toll Free: 87 PERMATEX
(877-376-2839)

10 Columbus Blvd., Hartford,
Connecticut 06106

6875 Parkland Boulevard, Solon
Ohio 44139

Technical Data Sheet

Ultra Slick™ Synthetic

Multi-Purpose Lubricant with PTFE

AAM Revised 03/04

PRODUCT DESCRIPTION

S.I.N.: 834-300

Permatex® Ultra Slick Synthetic Multi-Purpose Lubricant with PTFE is a GC/LB grease designed for wheel bearing and general chassis lubrication. It is a synthetic lubricant blend that can withstand temperatures from -40°F to +350°F. This high quality product can be used on any moving parts to provide better, longer lasting lubrication that is safe on many surfaces. Ultra Slick is available as a grease product and as an aerosol that sprays as an oil and dries to a grease consistency.

PRODUCT BENEFITS

- Provides a more reliable lubrication and outlasts petroleum based greases
- Developed to meet GC/LB test requirements for chassis and wheel bearing lubrication
- Withstands continuous temperatures from -40°F to +350°F
- Remains free flowing in freezing temperatures
- Contains PTFE to aid in extreme pressure applications
- Non-toxic
- Odorless
- Dielectric properties

TYPICAL APPLICATIONS

- Steering linkage fittings
- Chassis points
- Wheel bearings
- Door hinges
- Latch assemblies
- Seat tracks
- Dielectric grease
- Upper, lower ball joints
- Hood/trunk hinges/latches

DIRECTIONS FOR USE

For Grease

1. Make sure surfaces to be greased are free of dirt and rust.
2. Apply grease to surfaces.
3. Re-apply as necessary.

For Aerosol

1. Shake can well before using.
2. Make sure surfaces to be greased are free of dirt and rust.
3. Spray surfaces to be greased.
4. Use extension tube for hard to reach areas.
5. Re-apply as necessary.

PROPERTIES OF BASE MATERIAL

Chemical Type	Typical Value
Appearance	Synthetic hydrocarbon, PTFE resin
Specific Gravity	Translucent white gel
	0.80

Odor	Slight
Flash Point, COC, °C (°F)	204(400)
NLGI Grade	No. 2
Dropping Point ASTM D 2265 (°C)	>280
Worked Penetration D217	267
Water Washout @ 80°C D1264	
(% max.)	10
Oil Separation D1742 (% max)	1
Rust Protection D1743 (rating max)	Pass
Wear Protection D2266 (scar diameter max)	0.58
Four Ball Wear D2596	
load wear index, kgf min.	35
weld point, kgf min.	250
Dielectric Constant @ 1 KHz @ RT ASTM D 150	3.21
Dissipation Factor @ 1 KHz @ RT ASTM D 150	0.0023
Volume Resistivity @ RT ASTM D 257 (ohm-cm)	1.05×10^{14}

Data Ranges

The data contained herein are reported as typical values and/or ranges. Values are based on actual test data and are verified on a periodic basis.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a lubricant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
81943	11 oz. Net. Wt. aerosol
81944	14 oz. cartridge
81945	16 oz. tub
81946	3 oz. plastic tube
81905	5 gallon pail

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8° to 28°C (46° to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.